

## Test Report

No. KE/2015/81804

Date : Aug 24, 2015

Page 1 of 6

TAIXIANG RUBBER (SHEN ZHEN) CO., LTD.  
LISONG LANG INDUSTRIAL AREA GONG MING TOWN,SHENZHEN CITY,CHINA

The following sample(s) was/were submitted and identified by/on behalf of the client as :

### Report on the submitted sample said to be:

Sample Description : Chemical Material for Rubber  
Amount of Sample : One  
Buyer's Name / Division : Adidas Footwear  
Summary of Test Result : **Pass**  
Failure Test Items : ---  
Age Group : All Ages  
Material Name / Code : Vulcapellet SI-50  
Color Name / Code : Light Yellow  
Supplier Name : Taixiang Rubber (Shen Zhen) Co., Ltd.  
Country of Origin : China  
Country of Destination : ---  
Material Component : Vulcapellet  
Sample Classification : Rubber materials (201)  
Test Required Key Code No. : Key code 201 under Adidas A-01 Test Standard 2014  
Report Type : Full Test (FT)  
Full Test Report No. : ---  
(Only for SC\*/NT\*/IT\*/ST\*) : ---  
P.O. No. : ---  
Additional Information : ---  
Sample Received Date : Aug 19, 2015  
Sample Tested Date : Aug 19 ~ Aug 24, 2015  
Sample Submitted by : Taixiang Rubber (Shen Zhen) Co., Ltd.

Note: (SC\*)(NT\*)(IT\*)(ST\*) mark the full test reports No. ; (RT) this application just for T1 shoes factory; (SI) it is for supplier only and will not acceptable for adidas.

## Test Report

No. KE/2015/81804

Date : Aug 24, 2015


Page 2 of 6

**Summary of Test Result:** (Detail test results on next page)

Test Parameter	Test Method	Conclusion (Pass/Fail)
Extractable Heavy Metals	Extraction in acidic perspiration solution: DIN EN ISO 105 E04:2013 in acid solution, Analysis by ICP-OES: DIN EN ISO 12846:2012/ DIN EN ISO 11885:2009	Pass
Total Cadmium	Polymers: Pre-treatment: EN 1122:2002 Analysis by ICP-OES: DIN EN ISO 11885:2009	Pass
Total Lead	Non-metal parts: Pre-treatment: Microwave digestion with H <sub>2</sub> O <sub>2</sub> /HNO <sub>3</sub> Analysis by ICP-OES: DIN EN ISO 11885:2009	Pass
Organotin Compounds	ISO/TS 16179:2012	Pass
Σ Phthalates	dichloromethane with ASE Measurement with GC-MS	Pass
Σ Nonylphenol (NP), Octylphenol (OP), Nonylphenol ethoxylate (NPEO), Octylphenol ethoxylate (OPEO)	NP,OP: Solvent Extraction, Analysis by LC-MS NPEO,OPEO: Textiles: Draft DIN EN ISO 18254 (2014) Leather: Draft DIN EN ISO 18218-1	Pass
Regulated Polycyclic Aromatic Hydrocarbons (PAHs) of high concern	ZEK 01.4-08	Pass
Σ of Polycyclic Aromatic Hydrocarbons (PAHs)	ZEK 01.4-08	Pass

Sample Photo

## KE/2015/81804



  
**Jerry Tung / Asst. Manager**  
 Signed for and on behalf of  
**SGS Taiwan Limited**

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部分複製。  
 This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at [www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm) and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at [www.sgs.com/terms\\_e-document.htm](http://www.sgs.com/terms_e-document.htm). Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

## Test Report

No. KE/2015/81804

Date : Aug 24, 2015

Page 3 of 6

### Component List

Component No.	Component	Material
1	Light Yellow Chemical Material	Chemical

### Detail Test Results:

#### Extractable Heavy Metals

Test Method: Extraction in acidic perspiration solution - DIN EN ISO 105-E04:2013.  
Analysis by ICP-OES / ICP-MS - DIN EN ISO 11885: 2009 and DIN EN ISO 12846:2012.

	<u>Result</u>
	<u>1</u>
Cadmium	n.d.
Chromium	n.d.
Lead	n.d.
Mercury	n.d.
<b>Conclusion</b>	<b>PASS</b>

Note: n.d. = not detected  
\* = Exceeds the TLV

Client's Requirement	<u>Infants (ppm)</u>	<u>Adults (ppm)</u>	<u>Detection Limit (ppm)</u>
Cadmium	0.1	0.1	0.1
Chromium	1.0	2.0	1.0
Lead	0.2	1.0	0.2
Mercury	0.02	0.02	0.02

#### Total Cadmium

Test Method: Polymers: Acid digestion – EN 1122:2002  
Analysis by ICP-OES or AAS - DIN EN ISO 11885:2009.

	<u>CAS No.</u>	<u>Result</u>
		<u>1</u>
Total Cadmium	--	n.d.
<b>Conclusion</b>		<b>PASS</b>

Note: n.d. = not detected  
\* = Exceeds the TLV  
Detection Limit = 5 ppm

**Client's Requirement 40 ppm**

# Test Report

No. KE/2015/81804

Date : Aug 24, 2015

Page 4 of 6

## Total Lead

Test Method: Non metal: Pretreatment by Microwave digestion with H<sub>2</sub>O<sub>2</sub>/HNO<sub>3</sub>  
Analysis by ICP-OES: DIN EN ISO 11885: 2009

	<u>CAS No.</u>	<u>Result</u>
		<u>1</u>
Total Lead	--	n.d.
<b>Conclusion</b>		<b>PASS</b>

Note: n.d. = not detected  
\* = Exceeds the TLV  
Detection Limit = 5 ppm

**Client's Requirement 40 ppm**

## Organotin Compounds

Test Method: ISO/TS 16179:2012.

<u>Organotins</u>	<u>Result</u>
	<u>1</u>
Tributyltin (TBT)	n.d.
Triphenyltin (TPhT)	n.d.
Dibutyltin (DBT)	n.d.
Diocetyl tin (DOT)	n.d.
<b>Conclusion</b>	<b>PASS</b>

Note: n.d. = not detected  
\* = Exceed the TLV  
Detection Limit = 0.05 ppm (for individual compound)

### Client's Requirement:

**TBT Not Detected**  
**DBT 1 ppm**  
**TPhT 0.5 ppm (Infants) / 1 ppm (Adults)**  
**DOT 1 ppm**

## Test Report

No. KE/2015/81804

Date : Aug 24, 2015

Page 5 of 6

### Phthalates

Test Method: Dichloromethane with ASE. Analysis was performed by GC/MS

	<u>CAS No.</u>	<u>Result</u>
		1
Diisononylphthalate (DINP)	28553-12-0	n.d.
Di- <i>n</i> -octylphthalate (DNOP)	117-84-0	n.d.
Di(2-ethylhexyl)phthalate (DEHP)	117-81-7	n.d.
Diisodecylphthalate (DIDP)	26761-40-0	n.d.
Butylbenzylphthalate (BBP)	85-68-7	n.d.
Dibutylphthalate (DBP)	84-74-2	n.d.
Diisobutylphthalate (DIBP)	84-69-5	n.d.
Di-C6-8-branched alkylphthalates (DIHP)	71888-89-6	n.d.
Di-C711-branched alkylphthalates (DHNUP)	68515-42-4	n.d.
Di- <i>n</i> -hexylphthalate (DHP)	84-75-3	n.d.
Di-(2-methoxyethyl)-phthalate (DMEP)	117-82-8	n.d.
Dipentylphthalate (DPP)	131-18-0	n.d.
Total		n.d.
<b>Conclusion</b>		<b>PASS</b>

Note: n.d. = not detected  
 \* = Exceeds the TLV  
 Detection Limit:  
 DBP, BBP, DEHP, DIBP, DHP, DMEP, DNOP, DPP: 30 ppm (for individual compound).  
 DINP, DIDP, DHNUP, DIHP: 100 ppm (for individual compound)

**Client's Requirement 500 ppm (Total)**

### Σ of NP,OP, NPEO and OPEO

Test Method:  
 NP, OP: Solvent Extraction. Analysis was performed by LC-MS.  
 NPEO, OPEO: Textile: Draft DIN EN ISO 18254:2014.

	<u>Result</u>
	1
Nonylphenol (NP)	4.80 mg/kg
Octylphenol (OP)	n.d.
Nonylphenol ethoxylates (NPEO)	n.d.
Octylphenol ethoxylates (OPEO)	n.d.
Σ of NP,OP, NPEO and OPEO	4.80 mg/kg
<b>Conclusion</b>	<b>PASS</b>

Note: n.d. = not detected  
 \* = Exceeds the TLV  
 Detection Limit = 3 ppm

# Test Report

No. KE/2015/81804

Date : Aug 24, 2015

Page 6 of 6

**Client's Requirement**      **250 ppm (sum of NP, OP, NPEO and OPEO)**  
**10 ppm (NP)**  
**10 ppm (OP)**

## Polycyclic Aromatic Hydrocarbons (PAHs) and Regulated PAHs of High Concern

Test Method: ZEK 01.4-08. Analysis was performed by GC-MS.

	<u>CAS No.</u>	<u>Result</u>
		<b>1</b>
Naphthalene (NAP)	91-20-3	n.d.
Acenaphthylene (ANY)	208-96-8	n.d.
Acenaphthene (ANA)	83-32-9	n.d.
Fluorene (FLU)	86-73-7	n.d.
Phenanthrene (PHE)	85-01-8	n.d.
Anthracene (ANT)	120-12-7	n.d.
Fluoranthene (FLT)	206-44-0	n.d.
Pyrene (PYR)	129-00-0	n.d.
Benzo(j)fluoranthene (BjF)	205-82-3	n.d.
Benzo(a)anthracene (BaA)	56-55-3	n.d.
Chrysene (CHR)	218-01-9	n.d.
Benzo(b)fluoranthene (BbF)	205-99-2	n.d.
Benzo(k)fluoranthene (BkF)	207-08-9	n.d.
Benzo(a)pyrene (BaP)	50-32-8	n.d.
Indeno(1,2,3-cd)pyrene (IPY)	193-39-5	n.d.
Dibenzo(a,h)anthracene (DBA)	53-70-3	n.d.
Benzo(g,h,i)perylene (BPE)	191-24-2	n.d.
Benzo(e)pyrene (BeP)	192-97-2	n.d.
Total		n.d.
<b>Conclusion</b>		<b>PASS</b>

Note:            n.d. = not detected  
                  \* = Exceeds the TLV  
                  Detection Limit = 0.2 ppm (for individual compound)

**Client's Requirement:**

<b>Σ of PAHs</b>	<b>10 ppm (Total)</b>
<b>Benzo(a)anthracene (BaA)</b>	<b>1 ppm</b>
<b>Benzo(a)pyrene (BaP)</b>	<b>1 ppm</b>
<b>Benzo(b)fluoranthene (BbF)</b>	<b>1 ppm</b>
<b>Benzo(e)pyrene (BeP)</b>	<b>1 ppm</b>
<b>Benzo(j)fluoranthene (BjF)</b>	<b>1 ppm</b>
<b>Benzo(k)fluoranthene (BkF)</b>	<b>1 ppm</b>
<b>Chrysene (CHR)</b>	<b>1 ppm</b>
<b>Dibenzo(a,h)anthracene (DBA)</b>	<b>1 ppm</b>

\*\*\* End of Report \*\*\*

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部分複製。  
This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at [www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm) and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at [www.sgs.com/terms\\_e-document.htm](http://www.sgs.com/terms_e-document.htm). Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.